Swarland Black



Product Technical Information Sheet	
24170950	
Denton	
Extruded Wirecut	
Vertically perforated unit	
Black	
Sanded	
215 x 102.5 x 65	
400	
2.059	



Technical Properties to BS EN 771-1	
Size Tolerance (Mean/Range)	T2/R1
Percentage of Voids / Volume of Frogs	30
Gross Dry Density (kg/m3 /Tolerance)	1480(D1)
Compressive Strength (N/mm²)	40
Thermal Conductivity (W/(m·K)) λ10,dry,unit value (EN 1745 tabulated: S1)	P=90% 0.69
Durability Designation	F2
Water Absorption (%)	12
Initial Rate of Water Absorption (kg/(m²·min))	Min 1 Max 2.2
Active Soluble Salts	S2
Reaction to Fire	A1

Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the wienerberger Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.

- e. Wall and Landscaping enquiries
- **t.** 0161 491 8200
- w. wienerberger.co.uk

