


T: 01633 600 806 E: bricksbm@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 10/03/25

Hampton Vintage Stock Facing Bricks



The muted tones of red and orange partner perfectly with the aged appearance of the brick. Hampton Vintage also embraces the occasional subtle black brick running sporadically throughout, adding extra character to the blend.

DESCRIPTION	
Manufacturing Process	Vibro-compacted pressed concrete
Base Raw Material	Concrete
Green Guide Rating	A+
UKCA Marking/DOP	www.marshalls.co.uk/dop
NBS Specification	F10/215



T: 01633 600 806 E: bricksbm@marshalls.co.uk W: www.marshalls.co.uk/commercial

Date Created: 10/03/25

Hampton Vintage Stock Facing Bricks

ः

Marshalls

Creating Better Spaces

DUVOICAL DECREPTIES		ELIPTILED INFORMATION	
PHYSICAL PROPERTIES	045 400 05	FURTHER INFORMATION	
Work Dimensions (mm)	215 x 100 x 65	Cleaning & Maintenance	Cleaning & maintenance details are available on request
Nominal Dimensions (mm)	215 x 100 x 65	Efflorescence	Any product containing cement during its early life may exhibit a temporary white discolouration known as efflorescence. This is not a product fault and will gradually disappear with exposure to natural weathering and trafficking. Our manufacturing process involve the incorporation of advanced additives both within and on the surface of the brick. The amount of efflorescence emanating from the bricks can
Tolerances on Work Dimensions (mm)	Category D1 (+3-5mm in all directions)		
Durability (Freeze-thaw)	Frost Resistant		
Gross Density	1900kg/m³		
Thermal Conductivity (K value)	1.11 W/mK (dry); 1.24 W/mK (@3%); 1.33 W/mK (@5%)		
Water Vapour Permeability (?)	5/15µ (Tabulated from EN 1745)		
Shear Bond Strength (N/mm2)	0.15N/mm² (Tabulated from EN 998-2: 2003, Annex C)		
Dimensional Stability	<0.6 mm/m		
Compressive Strength (Mpa)	>22.5N. Air dry	VA/ 41	thus be classed as minimal
SPECIFICATION		Weathering	It should be appreciated that with all products weathering and
Emission of Asbestos	No content		site conditions can cause shade variation to appear across the surface of individual units. This does not in any way affect the performance of the units and any such variation will diminish over a period of time as the product matures.
Reaction to fire	Euroclass A1		
Selection Of Mortar	Spacing and width should be based on the guidelines provided in BS EN 1996 - Design of Masonry Structures		
Dangerous Substances	No performance declared	Product Evolution	
Movement Joints	Spacing and width should be based on the guidelines provided in BS EN 1996 - Design of Masonry Structures	Product Evolution	The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details
Moisture Movement	<0.45mm/m		
APPLICATION			Marshalls reserves the right to amend the technical information
Eminently suitable for use below dpc in foundations, boundary walls and externally above ground level up to sulphate resistance class DS2, regardless of the severity of exposure. Manufactured and tested in accordance with BS EN 771-3: 2011+A1 2015: Specification for Masonry Units: Aggregate Concrete Masonry Units		as deemed necessary and in accordance with the relevant national and international standards without notice.	
	Contact Us	As many of these products are made to order for specific markets, please obtain further details on specification details, product availability, pack sizes and weights from your local Edenhall Sales Office, or call our Head Office.	
SUPPLY			
Units Per Pack	416		
Packaging	Self contained packs, palletised with polythene stretch hood and with or without banding straps dependant on supply works		