## NEWNHAM YELLOW ANTIQUE CBP-OLI-CY7

## TEXTURE, TYPE & COLOUR

Handmade facing bricks for interior and exterior use in decorative or construction walls.

Newnham Yellow Antique; This clay facing brick has the Rustic charm and informal style typical of bricks produced at the Olivier Bricks factory. A slightly muted mix of yellow and buff colours with white touches. — a sympathetically balanced yellow/buff brick with the occasional use of a blackened brick, like punctuation, creates a visible pause.

## TECHNICAL CHARACTERISTICS

The facing bricks are delivered with the following characteristics, in accordance with the CE and Benor marks:

NEN-EN 771-1, April 2013, and NEN-EN 771-1/A1, March 2005 Category I, HD clay bricks.

Dimensions may vary depending on the production. For the most recent version see www.camtechbp.co.uk. This document is not binding and annuls all previous publications. The manufacturer reserves the right to change the product range and characteristics. The user must always check that they have the most recent descriptive text.



FACTORY: OLIVIER BRICKS



NEN-EN 771-1, April 2013, and NEN-EN 771-1/A1, March 2005 Category I, HD clay bricks

Length	: 215 mm, T1 (+/- 6 mm), R1 (9 mm)
Width	: 102 mm, T1 (+/- 4 mm), R1 (6 mm)
Thickness	: 65mm, T1 (+/- 3 mm), R1 (5 mm)
Appearance	: Soft Mud Tumbled, Euro group 1
Average compressive strength	: >15 N/mm2
Dimensional stability	: NPD
Bond strength	: 0.15 - 0.30 N/mm2
Active soluble salts	: S2
Reaction to fire	: Euro class A1
Water absorption	: <24% m/md
Initial rate of water absorption	: IW4 strong suction, >4.0 kg/m2.min
Water vapour diffusion coefficient	:5/10
Gross dry density	: 1450 kg/m3, D1 (10%, +/- 145 kg/m3)
Thermal conductivity	: 0,41 W/mK
Freeze/thaw resistance	:F2

Production Reference code: Olivier Yellow-7

	,
Width	: 102 mm, T1 (+/- 4 mm), R1 (6 mm)
Thickness	: 65mm, T1 (+/- 3 mm), R1 (5 mm)
Appearance	: Soft Mud Tumbled, Euro group 1
Average compressive strength	:>15 N/mm2
Dimensional stability	: NPD
Bond strength	: 0.15 - 0.30 N/mm2
Active soluble salts	: S2
Reaction to fire	: Euro class A1
Water absorption	: <24% m/md
Initial rate of water absorption	: IW4 strong suction, >4.0 kg/m2.min
Water vapour diffusion coefficient	: 5/10
Gross dry density	: 1450 kg/m3, D1 (10%, +/- 145 kg/m3)
Thermal conductivity	: 0,41 W/mK
Freeze/thaw resistance	: F2

Call Camtech: 01763 262006



We want to help you make informed decisions and find the right solution for your business, customers or project; after all, it's much more than just a product, Right!



CAMTECH BUILDING PRODUCTS LTD p. Camtech House, 21 Jarman Way Royston, Herts, SG8 5HW. UK

t. +44 (0)1763 262006 e. info@camtechbp.co.uk w. camtechbp.co.uk